



Antibacterial Ceramic Ball

Instruction For Use

I. Specifications: 4.5~5.5mm, 6~8mm

Color: white

II. Main Ingredients:

Nano silver powder: 1%, Maifan Stone: 50~60%

Zinc oxide: about 2.5%, Kaolin: 10~15%

Far infrared powder: 10%, Clay with top grade: 20~30%

Others: 5~10%

III. Main Features:

Resisting and killing golden staphylococcus $\geq 90\%$

Resisting and killing colibacillus $\geq 90\%$

Amount of generating negative ions: 150~300p/s.cm³

PH of soaking water solution: 7.2~7.8

Insoluble, gradually releasing mineral substance

IV. Packing, Storage and Transportation

Plastic bag, 10kg/bag or 25kg/bag, or customized

Keep from raining, and avoid moisture. Stored in dry place.

V. Instruction For Use:

1. Should wash with clean water for two times in the first, then can be directly used for treating drinking water. **Note:** the highest using temperature is at 95°C
2. Before bathing, in order to prevent the small granule ceramic balls sliding from the nozzle and cause bruise phenomena of the human body it's better to put one piece of PP cotton filter membrane with about 5 μ m inner diameter inside.
3. It's better not to use acidic liquid shampoo and bath lotion for avoiding that the neutralization between the alkalescence water after treated by the ceramic balls and acidic bath liquid and influence the bath effect.